



GLOBAL TIMBER

## Data sheet - Thermo Ash decking & cladding

April 2022



<b>Species:</b> Ash ( <i>Fraxinus excelsior</i> ) with origin in Europe
<b>Moisture content:</b> Kiln dried to about 8% +/-2%
<b>Weight:</b> About 550 kg/m <sup>3</sup>
<b>Color:</b> Dark brown (color difference cannot be avoided)
<b>Expected lifespan:</b> Decking: 40 years, cladding: 50 years
<b>Stability:</b> Class 1 (scale 1-5 = 1 being the best)
<b>Color extraction:</b> Rare

### Application

- External product for e.g. decking, stairs, bridges, cladding, that are all above ground.

### Quality

- Prime quality 1 face. Natural defects are occasionally allowed – such as knots, cracks, discoloration, pinholes etc.

### Tolerance

- Thickness about +1/-1 mm and width about +/-2 mm at delivery.

### Grain

- Straight grain

### Storage

- Store under a roof with good ventilation and in the original bundles (avoid sunlight).

